



Fig. 5206RF

Standard Material Specifications		
No.	Description	Materials
1	Body	ASTM A216 GR WCB
2	Bonnet	ASTM A216 GR WCB
3	Wedge Gate	ASTM A216 GR WCB + 13% Cr.
4	Seat Ring	ASTM A515 GR 70
5	Stem	ASTM A276 Type 410
6	Yoke	ASTM A216 GR WCB
7	Stem Nut Retainer	ASTM A36
8	Grease Fitting	Commercial Steel
9	Stem Nut	ASTM B 148 UNS C95600
10	Eyebolt	Alloy Steel
11	Eyebolt Nut	ASTM A307
12	Gland	ASTM A515 GR 70
13	Packing Bushing	ASTM A108 GR 1020
14	Eyebolt Pin	Alloy Steel
15	Stem Packing	Graphite
16	Bonnet Bushing	ASTM A276 Type 410
17	Bonnet Gasket	Spiral Stainless Steel 304/Graphite
18	Bonnet Stud	ASTM A193 GR B7
19	Bonnet Stud Nut	ASTM A194 GR 2H
20	Handwheel	ASTM A197
21	Handwheel Nut	ASTM A108 GR 1020
22	Set Screw	Alloy Steel
23	Retainer Bolt	Alloy Steel
24	Retainer Bolt Nut	ASTM A307
25	Yoke Stud	Alloy Steel
26	Yoke Stud Nut	ASTM A307
*27	Identification Plate	Stainless Steel

* Not Shown

*The above part lists're for size 8" up

Dimensions

D	mm	50	65	80	100	150	200	250	300	350	400
Nominal Diameter	inch	2	2 1/2	3	4	6	8	10	12	14	16
A	mm.	215.9	241.3	282.5	304.8	403.2	419.1	457.2	501.65	762	838
B	mm.	473	568	546	673	935	1083	1314	1594	1730	1924
C	mm.	203.2	203.2	254	254	355.6	406.4	508	508	660	711
E	mm.	165.1	190.5	210	254	317.5	381	444.5	520.7	584	648
Weight	kg.	26	47	43	68	136	212	343	491.5	907	1202

Trim

Trim		Internal Parts		
API	Walworth	Seat Ring	Gate (Disc)	Stem Hanger Pin Bonnet Bushing
8	*UT	Stellite No. 6	13% Cr. (SS 410)	13% Cr. (SS 410)
5	HF	Stellite No. 6	Stellite No. 6	13% Cr. (SS 410)

*UT-Trim (Universal Trim)

Test Pressures

For valves having flanges or butt welding ends to ANSI Class 300 Standards.

	shell Hydrostatic	Seat* Hydrostatic	Seat*Air under Water
lb/in ²	1125	825	100
MPa	7.7	5.7	.7

*Seat leakage rate: All valves meet BS 6755 Part 1 leakage rate A (No visible leakage for duration of test).

Pressure - Temperature Ratings

		MAXIMUM ALLOWABLE NON-SHOCK WORKING PRESSURE IN PSIG BY CLASS					
°F Temperature °C		150	300	400	600	900	1500
-20 to 100	-29 to 38	285	740	990	1,480	2,220	3,705
200	93	260	675	900	1,350	2,025	3,375
300	149	230	655	875	1,315	1,970	3,280
400	204	200	635	845	1,270	1,900	3,170
500	260	170	600	800	1,200	1,795	2,995
600	316	140	550	730	1,095	1,640	2,735
650	343	125	535	715	1,075	1,610	2,685
700	371	110	535	710	1,065	1,600	2,665
750	399	95	505	670	1,010	1,510	2,520
800	427	80	410	550	825	1,235	2,060
850	454	65	270	355	535	805	1,340
900	482	50	170	230	345	515	860
950	510	35	105	140	205	310	515
1000	538	20	50	70	105	155	260

For prolonged usage at temperatures above 800°F (427°C), consideration should be given to the possibility of graphite formation in Carbon Steel.

*last updated 03/16

