



The Softest PTFE material for applications where just minimal surface pressure are possible. Excellent compensation of Irregularities of the Sealing Surface.

UKL Soft-Plus is a 100% pure expanded PTFE Material manufactured with special process that produces a uniform and highly fibrillated microstructure with a lot of fibers running in multidirection.

UKL Soft-Plus possesses universal resistance against common chemicals, except melted alkali metal, fluorine at liquid and gas states. It is free from asbestos and other lung-intruding materials.

UKL Soft-Plus is an asbestos free material and meets the FDA requirements, doesn't have any corrosion and is able to be stored without any time limits. Also suitable for oxygen applications.

Properties:

Color: White

Thickness: 1.5mm and 3mm (other thicknesses

available on request)

Size: 1500mm x 1500mm (other sizes available on

request)

Temperature range: Suitable for -240°C up to +260°C. for short

period up to 315°C

Operating pressure: From vacuum to 3,000 psi

Chemical resistance: Chemically inert against all substances (pH

0- 14), including the most aggressive acids and strong caustic alkaline solution (lyes).


The only exceptions are molten


alkali metals and elemental fluorine at high

temperature and pressure.

General Features:

- 100% Pure P.T.F.E.
- Good sealability
- Good flexibility
- Highly compressible
- Resistant to creep and cold flow
- Easy to cut and install
- Low compressive load to seal
- Can seal rough or damaged flanges.





The fields of decision

- (1) If your operating temperatures and pressures fall within this field, a technical examination is normally unnecessary.
- ② If your operating temperatures and pressures are within this field, a technical examination is recommended.
- (3) If your operating temperatures and pressures are within this "open" field, a technical examination is recommended.

Typical values for 1.5mm thickness

Compressibility ASTM F 36	%	60	
Recovery ASTM F 36	%	12	
Stress relaxation DIN52913 30 Mpa,16 h / 150 °C	Мра	15	
Tensile strength DIN 52910	N/mm²	25	
Sealability ASTM F 37-B (nitrogen) @60psig	ml/hr	0.16	
Density	gm/cm3	0.85	